

DELTA Prime 2K SF (Solvent Free)

TWO COMPONENT EPOXY BASED SOLVENT FREE PRIMER

DESCRIPTION

DELTA Prime 2K SF Primer is a two component, solvent-free, medium viscosity epoxy primer specifically designed for sealing and priming concrete substrates. **DELTA Prime 2K SF** is ideal for solidifying porous and weak concrete substrates and can be combined with quartz sand to make a fast curing hard patch repair material.

FEATURES

- ✓ Formulated at 1:1 ratio by volume for easy application with brush, spray or roller.
- ✓ Penetrates deeply into concrete surface
- ✓ Solvent-free. Non-hazardous.
- ✓ Exceptional adhesion to correctly prepared concrete, steel and most common construction substrates.

TYPICAL USES

- ✓ As a penetrating concrete densifier and primer prior to the application of VIP-DELTA protective linings.
- ✓ As a patch repair material when combined with either quartz sand or **DELTA Prime Filler**.
- ✓ As a base coat for VIP-DELTA floor coatings.

PRODUCT INFORMATION

| PHYSICAL PROPERTIES | DATA | |
|-----------------------------------|-------------|--|
| Mixing Ratio | | 1:1 |
| Tack free time | | @ 30°C approximately 1 - 2 hours |
| Coverage on Concrete | | 1 st coat approximately 250 grams / m ² 2 nd coat approximately 150 – 175 grams / m ² |
| Overcoat Window | | Up to 20°C maximum 72 hours Up to 21-35°C maximum 60 hours @ 35°C plus maximum 48 hours |
| Hardness (Shore D) | | 70 - 80 |
| Temperature range for application | | +5 to +50°C |
| VOC Content | ASTM D-1259 | Zero |
| Solids content - % | ASTM D-2697 | 100 % |

| PHYSICAL PROPERTIES | DATA | |
|--------------------------|----------------------------|---------------------------------|
| Pull off strength – mPa | ASTM D-4541 | Steel: ≥ 6 Concrete: ≥ 1.5 |
| Impact Resistance [J/mm] | DIN EN 10290-2004 Class: A | 23° C: 9,0 -5° C: 7,0 |
| Surface resistance [Ohm] | DIN IEC 60167 | ≥ 1,0*10 ¹¹ |
| Volume resistance [Ohm] | DIN IEC 60093 | ≥ 1,0*10 ¹¹ |

SURFACE PREPARATION

The substrate should be prepared according to the final coating manufacturer`s instructions specific for the final coating product. However, as a general guide; concrete substrate should be free from all contaminants, loose or flaky material and should be in a sound condition. Steel substrates should generally be grit blasted to a class 2 ½ blast with a surface profile of between 50 – 100 microns. For other substrate types refer to coating manufacturer`s guidelines.

MIXING & APPLICATION

DELTA Prime 2K SF is supplied in a pre-weighed 2 component pack consisting of a Base component and a Hardener component. The contents of the hardener pack should be emptied into the base pack completely, and mixed with slow speed light duty mixing drill and paddle. The mixed product can then be applied on the prepared substrate using a brush or roller.

EQUIPMENT CLEANING

Equipment can be cleaned with paint thinner and common solvents immediately after use. Note that hardened material can only be removed mechanically

STORAGE

Approximately 12 months from the date of manufacture, when kept in original containers under standard storage conditions.

APPLICATION NOTES

Before using both components should be individually stirred and then component B has to be filled into component A completely and mixed carefully with a power drill attached to a stirring paddle.

The primer should be applied preferably by roller or alternatively by spraying in a conventional way with an airless sprayer.

IMPORTANT: *DELTA Prime 2K SF* should be completely dry before over coating.

All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the user's responsibility to satisfy himself, by his own investigations and testing, the suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. These products require specialized equipment and skills to apply. It is the purchaser's responsibility to ensure that they have the necessary equipment, skills and experience to apply these products. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Technical and application information is provided for the purpose of establishing a general profile of the material and application parameters. Test performance results were obtained in a controlled environment and VIP-DELTA Coatings International LLC makes no claim that these tests or any other tests can be accurately reproduced in all environments.

The rights of the purchaser regarding the quality of our materials follows completely our general terms and conditions. For requirements, which exceed the scope of the above-mentioned applications please contact VIPDELTA technical staff.

VIP-DELTA Coatings International LLC reserves the right to change or modify the details and data contained herein at any time.

Valid is only the actual version of this technical data sheet in each case.

* VIPDELTA recommends that in all applications involving chemicals a pre-test of the lining's suitability in the customer's application is conducted. Consult with VIPDELTA Technical Team.

© Copyright, VIP-DELTA Coatings International LLC, DeltaPrime 2K SF

Version: October 2019-001